# Hess Grade 6/0N

PARTICLE SIZE SPECIFICATION GRADE 6/0N		
SIZE		ALLOWABLE
MICRON [MM]	U.S. MESH	PERCENT PASSING
106 [0.106]	140	100
90 [0.090]	170	99-100
75 [0.075]	200	95-100
63 [0.063]	230	86-98
45 [0.045]	325	55-65
TEST METHOD: ASTM C136-06		

#### LOOSE BULK DENSITY GRADE 6/0N

52 lb/per cubic foot [832.9 kgs/per cubic meter] (ASTM C29)

#### CHEMICAL ANALYSIS AND PHYSICAL PROPERTIES

Chemical Name: Amorphous Aluminum Silicate

# TYPICAL ANALYSIS Silicon Dioxide: 76.2%

Aluminum Oxide: 13.5%

• Ferric Oxide: 1.1%

• Ferrous Oxide: 0.1%

Sodium Oxide: 1.6%

Calcium Oxide: 0.8%

Titanium Oxide: 0.2%

Crystalline Si02: None

Moisture: <1.0%</li>

Detected

Magnesium Oxide: .05%

Potassium Oxide: 1.8%

#### **GENERAL PROPERTIES**

- Appearance: White powder
- Hardness (MOHS): 6
- pH: 7.2
- Radioactivity: None
- Softening Point: 900 degrees C
- Water Soluble Substances: 0.15%
- Loss on Ignition 5%
- GE Brightness: 84
- Specific Gravity: 2.4
- Reactivity: Inert (except in the presence of calcium hydroxide or hydrofluoric acid)



(208) 766-4777 x111 • email: rd@hesspumice.com www.**hesspumice.com** 

*Mining and refining the purest commercial deposit of white pumice on the planet.* 

ISSUE 2000 REVISION 4/2001 REVIEW 7/2021

# DESCRIPTION

Amorphous (non-crystalline) in structure and composed primarily of aluminum silicate, pumice is a naturally calcined volcanic glass foam consisting of highly vesicular strands permeated with tiny air bubbles. It is these frothy, friable glass vesicles that, when carefully refined to various grades, give pumice its unique and infinitely useful qualities.

# **GRADE APPLICATIONS**

Used for: plastics tumbling.

# **PACKAGING OPTIONS**

- 1 lb or 1 kg resealable bags
- 44 lb [20 kg] pails
- 55 lb [25 kg] bags (palleted)
- 100 lb [45 kg] drums
- Bulk shipped in rail car or tractor trailer

# **DISTRIBUTOR NETWORK**

We have stocking distributors in 23 countries on every continent except Antarctica, allowing us to deliver pumice quickly and economically worldwide.

